

The glass material must contain at least 5% boron oxide to be termed “borosilicate glass”. Other types of glass with less than 5% is often called flint glass or sodium glass.

Printed from the Chrom Resource Center

Copyright 2024, All Rights Apply

MicroSolv Technology Corporation

9158 Industrial Blvd. NE, Leland, NC 28451

tel. (732) 380-8900, fax (910) 769-9435

Email: customers@mtc-usa.com

Website: www.mtc-usa.com