



The differences in ion content between clear and amber borosilicate glass vials – Tech Information

Clear glass can be made of either Type-33 or N51A glass while amber is always made with N51A glass. There is an ASTM method that exists and defines what properties the glass must have in order to be called Type 33 or 51.

Ions	Type I clear glass(33)	Type I amber (51) glass
Na	0.3-0.5	0.4-1.4
K	ND	ND-0.02
Ca	ND	ND-0.1
Mg	ND	
Al	ND	ND-0.5
Fe	ND	ND
Ba	ND	ND-0.2
Zn	ND	ND
Mn	ND	ND
Si	ND	ND-5

Results are in $\mu\text{g} / \text{ml}$
ND = Non detectable

Printed from the Chrom Resource Center

Copyright 2024, All Rights Apply

MicroSolv Technology Corporation

9158 Industrial Blvd. NE, Leland, NC 28451

tel. (732) 380-8900, fax (910) 769-9435

Email: customers@mtc-usa.com

Website: www.mtc-usa.com