



## How resistant are the ultra fine point markers to smearing – FAQ

The markers were tested on standard glass autosampler vials and the writing was found to be completely smear-resistant when using a dry cloth, after waiting a short while ( about 30 seconds) for the ink to dry.

If you wish to remove the writing however, this can be accomplished with a solvent such as methanol, acetone, or isopropanol.

Printed from the Chrom Resource Center

Copyright 2024, All Rights Apply

**MicroSolv Technology Corporation**

9158 Industrial Blvd. NE, Leland, NC 28451

tel. (732) 380-8900, fax (910) 769-9435

Email: [customers@mtc-usa.com](mailto:customers@mtc-usa.com)

Website: [www.mtc-usa.com](http://www.mtc-usa.com)