



Additional specifications for HPLC low pressure PFA tubing – Tech Information

Some extruders of PFA tubing list the specifications below on their website.

Physical

Density (g/cc): 2.12 – 2.17

Water Absorption (%) < 0.03 Standard Percent Crystallinity (%): 48 – 70

Refraction Index: 1.350 Radiation Resistance (MRad): 1 – 10 Oxygen Index (%): > 95

Mechanical

Hardness, Shore D: 55 – 60

Ultimate Tensile Strength (MPa): 25 – 28

Elongation at Break (%): 250 – 420

Modulus of Elasticity (GPa): 0.48

Flexural Modulus (GPa): 0.50 – 0.70

Coefficient of Friction: 0.04 – 0.20

Electric

Volume Resistivity (Ω -cm): 1.0×10^{18}

Dielectric Constant: 1 MHz 1.9 – 2.1

Dielectric Strength (V/mil): 2030

Thermal

Thermal Conductivity (W/m-K): 0.15 – 0.25

Maximum Service Temp, Air (°C): 260

Minimum Service Temp, Air (°C): -200

Melt Temp (°C): 300 – 315

Glass Temp (°C): 90

Decomposition Temp (°C): 475

Coefficient of Thermal Expansion, linear 20° ($\mu\text{m}/\text{m}\text{-}^\circ\text{C}$): 120 – 140

Click [HERE](#) for Low Pressure, HPLC Tubing Ordering Information

Printed from the Chrom Resource Center

Copyright 2024, All Rights Apply

MicroSolv Technology Corporation

9158 Industrial Blvd. NE, Leland, NC 28451

tel. (732) 380-8900, fax (910) 769-9435

Email: customers@mtc-usa.com

Website: www.mtc-usa.com